

Diameter [mm]	Circumf. [inches]	Weight [kg/100 m]	S 60 Breaking strength [t]	S 75 Breaking strength [t]
10	1 ¼	5,7	7.2	9.0
12	1 ½	8	10.4	13.0
14	1 ¾	11	14.1	17.0
16	2	14	17.8	22.0
18	2 ¼	18	22.4	28.0
20	2 ½	22	27.7	34.0
22	2 ¾	26	33.6	42.0
24	3	31	39.8	48.0
26	3 ¼	36	47.0	58.0
28	3 ½	42	54.4	68.0
30	3 ¾	48	62.5	78.0
32	4	55	71.5	89.04
34	4 ¼	62	80.5	100.0
36	4 ½	69	89.0	111.0
38	4 ¾	77	98.5	123.0
40	5	86	108.0	136.0
42	5 ¼	94	120.0	148.0
44	5 ½	104	132.0	168.0
46	5 ¾	113	144.0	182.0